

Single Coated Polyester Film Tapes 8995 and 8996

Product Data Sheet

May 2011

Supersedes: NEW

Product Description

3M™ General Purpose Polyester/Silicone Tapes 8995 and 8996 are polyester tapes with a silicone adhesive designed for high temperature applications. They can be used to break flash in composite bonding as well as splicing silicone and non-silicone coated papers and films

Key Features

3M™ Single Coated Polyester/Silicone Tapes 8995 and 8996 are primarily used as a masking tapes in the powder coating industry and as splicing

Physical Properties

Adhesive Type	Silicone	
Backing	Polyester	
Colour	Blue	
Release Liner	None	
Thickness (AFERA 5006)	8995 0,060 mm	
	8996 0,085 mm	

Performance Characteristics

Peel Adhesion (AFERA 5001)	8995	3,0 N/cm
	8996	3,5 N/cm
Tensile Strength (AFERA 5004)	8995	40 N/cm
	8996	70 N/cm
Elongation (AFERA 5004)	8995	90%
	8996	85%
Short term Temperature Performance	180°C –	200°C

Storage	Store in clean dry place. Temperature of 21 °C and 50 percent relative humidity are recommended.
Shelf Life	3M 8995 and 8996 Single Coated Polyester Film Tapes have a shelf life of 12 months from date of dispatch by 3M when stored in the original carton at 21°C (70°F) & 50 % Relative Humidity.

For Additional Information		

To request additional product information see address below. 3M Svenska AB, Industri, 191 89 Sollentuna

Important Notice

All statements, technical information and recommendations contained in this document are based upon tests or experience that 3M believes are reliable. However, many factors beyond 3M's control can affect the use and performance of a 3M product in a particular application, including the conditions under which the product is used and the time and environmental conditions in which the product is expected to perform. Since these factors are uniquely within the user's knowledge and control, it is essential that the user evaluate the 3M product to determine whether it is fit for a particular purpose and suitable for the user's method or application. All questions of liability relating to this product are governed by the terms of the sale subject, where applicable, to the prevailing law

Values presented have been determined by standard test methods and are average values not to be used for specification purposes. Our recommendations on the use of our products are based on tests believed to be reliable but we would ask that you conduct your own tests to determine their suitability for your applications.

This is because 3M cannot accept any responsibility or liability direct or consequential for loss or damage caused as a result of our recommendations

3M is a trademark the 3M Company



3M Svenska AB Industri

Bollstanäsvägen 3 191 89 Sollentuna Tel: 08-92 22 50 Fax: 08-92 22 88

E-post: kundservice@mmm.com

www.3M.se/tejp